

## Typical Properties & Specification

Product Number	PBPRO		
Material Type	Expanded Polypropylene		
Part Format	Interlocking panel		
Part Size, nominal net coverage	24.15 sq ft per panel (2.24 sq m)		
Part Thickness, nominal	1.00 in (25 mm)		
Part Length, nominal	73.5 in (1867 mm)		
Part Width, nominal	49.0 in (1245 mm)		
Part Weight, nominal	5.87 lbs per panel		

Property	Typical Value	Specification	
Tensile Strength <sup>1</sup>		> 80 psi	ASTM D3574-08 Test E
Tensile Elongation <sup>1</sup>	26%	> 20%	ASTM D3574-08 Test E
Compression Strength <sup>2</sup>			ASTM 3575-08 Test D
@ 25% strain	41 psi	> 35 psi	
@ 50% strain	56 psi	> 50 psi	
Compression Set 3	5%	<7.5%	Brock Test Method
35psi for 30 minutes – Set after 24 hrs	0.0	17.07	Brook rook mounds
Coefficient of Linear Thermal Expansion <sup>4</sup>			
per 1º C change	0.065 mm/m	< 0.10 mm/m	ASTM D696
Thermal Conductivity (Lambda Value) <sup>5</sup>	~ 0.0377 W/mK	Information Only	EN 12667:2001 / ISO 7345
Thermal Resistance (R Value) 5	~ 0.64 Km²/W	Information Only	EN 12667:2001 / ISO 7345
Water Absorption <sup>6</sup>			DIN 534 28
After 24 hrs immersion	~ 1%	≤ 1%	
Water Permeability 7	720 in / hr	> 500 in / hr	ASTM 1551 Suffix-DIN 18-035, Part 6
* Lateral Transmissivity 8			ASTM D4716-14
Flow Rate @ .005 Gradient	0.57 gpm/ft	0.50 gpm/ft	
Flow Rate @ .0075 Gradient	0.74 gpm/ft	-	
Flow Rate @ .01 Gradient	0.90 gpm/ft	-	
Head Injury Criterion 1,000 – Critical Fall Height <sup>9</sup>	1.21 m	1.2 m	ASTM F3146-18, Procedure A
Gmax <sup>9</sup>	89 g	<95 g	ASTM F355-16 Missile A
Shock Absorption <sup>9</sup>	63% / 64%	> 60%	ASTM F3189-17 / EN14808:2005
Vertical Deformation <sup>9</sup>	6.2 mm	< 7 mm	ASTM F3189-17 (Advanced Artificial Athlete)
Vertical Deformation <sup>9</sup>	2.8 mm	< 3.5 mm	EN14809:2005 (Artificial Athlete)
Resistance to Chemicals 10	1/2	≤ 2	ASTM F925
Resistance to Acid and Alkaline Liquids 11			EN 14030:2010
% tensile strength loss - 100yr model	0% after 12 days	0% after 12 days	ISO 12960:1998
Resistance to Oxidation (Accelerated Aging) 12			EN ISO 13438:2004
% tensile strength loss - 100yr model	6% after 56 days @ 110°C	6% after 56 days @ 110°C	
Microbiological Analysis 13			
bacteria resistance 13	No growth	No growth	ASTM G22
fungi resistance 14	No growth	No growth	ASTM G21
Environmental Standards Testing			
Cradle to Cradle 15	Certified	Certified	Cradle to Cradle Products Innovation institute
Heavy Metals 16 - 17	Compliant to EPA human health	Compliant to EPA human health	
VOC's 16 - 17	standards, surface water quality, groundwater quality	standards, surface water quality, groundwater quality	EPA 6010B, 7470A, 7471A
SVOC's 16 - 17	groundwater quality	groundwater quality	EPA 8260B EPA 8270C
California Title 22 17	Compliant	Compliant	California Code of Regulations, Title 22,
California Proposition 65 18	Certified	Certified	Division 4.5, Chapter 11 California Proposition 6/614

## DATA ARE TYPICAL PROPERTIES ONLY. THIS DOCUMENT DOES NOT CREATE ANY WARRANTY, EXPRESS OR IMPLIED

 $The \ Brock \ PowerBase \ PRO, \ PowerBase \ YSR, \ Performance \ Base \ F24, \ Performance \ Base \ F20$ 

<sup>\*</sup> Note that ASTM D4716 flow rate and hydraulic transmissivity values are not an indication of overall athletic field drainage performance.

<sup>1-18</sup> Test reports available upon request